

Directions for Stainless Steel Rust Remover

Read all directions thoroughly before beginning.

DILUTIONS

For heavy soil or rust use as supplied. May be diluted with as much as a 5:1 ratio with water depending on degree of soiling.

TO REMOVE RUST AND TARNISH:

- 1. **Apply Rust Remover** with a brush. Allow to dwell. Do not let the rust remover dry on the surface. Re-wet if necessary.
- Check after 15-20 minutes to see if the rust is removed. To check a small area, agitate the rust remover on the surface with a brush or Prep Pad going with the direction of the grain to remove the rust in the grooves of the stainless steel. Repeat Steps 1 and 2 as necessary until rust is removed.
- 3. **Rinse well**. Once the rust is removed, rinse with fresh water. Use a brush to aid in rinsing as needed. Rinse twice.
- 4. Neutralize immediately and coat with Everbrite Coating appropriate to protect the surface. The Rust Remover is acid based; the surface must be neutralized. Follow the Directions for Everbrite™ Coatings on Unpainted Metals beginning with Neutralize, then Solvent Wipe & Applying Coating.